



Enviro Liner® 1020

Property	ASTM Test Method	EL 1020
Thickness (min. avg)	D5199	20 mil 0.5 mm
Thickness, Lowest Individual of 10 values		18 mil 0.45 mm
Sheet Density (max)	D792	0.939 g/ml
Tensile Properties (min. avg) ASTM D 6693 Type IV; Gage length - break: 2" Gage length - yield: 1.3"	Tensile Strength @ Break	76 ppi 13 N/mm
	Tensile Elongation @ Break	800%
Tear Resistance (min. avg)	D1004	11 lbs 50 N
Puncture Resistance (min. avg)	D4833	28 lbs 120N
High Pressure Oxidative Induction Time (HPOIT)	D5885	> 400 minutes
Carbon Black Content	D1603	2.0 - 3.0%
Carbon Black Dispersion	D5596	CAT 1 or 2

Typical Roll Dimensions (Rolls dimensions may vary \pm 1%)

Roll Width	-	148" or 3.75 m
Roll Length	-	2000 feet or 609.6 m

Disclaimer: Layfield disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.